




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

| | | | |
|---|--|---|---|
| (51) International Patent Classification 5 : C08F 2/00, B01J 19/00 C08F 2/34 | | A1 | (11) International Publication Number: WO 93/24533 |
| | | | (43) International Publication Date: 9 December 1993 (09.12.93) |
| (21) International Application Number: PCT/US93/05051 | | (74) Agent: SROKA, Frank, J.; Amoco Corporation, Patents and Licensing Department, Mail Code 1907, P. O. Box 87703, Chicago, IL 60680-0703 (US). | |
| (22) International Filing Date: 27 May 1993 (27.05.93) | | | |
| (30) Priority data: 07/889,820 29 May 1992 (29.05.92) US | | (81) Designated States: CA, HU, JP, KR, RU, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). | |
| (71) Applicant: AMOCO CORPORATION [US/US]; Mail Code 1907, Patens and Licensing Department, P.O. Box 87703, Chicago, IL 60680-0703 (US). | | <p>Published</p> <p><i>With international search report.</i></p> <p><i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p> | |
| (72) Inventors: BUCHELLI, Alberto ; 12007 Ridgewood Canyon, Houston, TX 77059 (US). CARACOTSIOS, Malamas ; 1372 East Gartner Road, Naperville, IL 60540 (US). | | | |

(54) Title: POLYMERIZATION OF ALPHA-OLEFINS



(57) Abstract

An advanced control method is disclosed for the polymerization of an alpha-olefin in a substantially horizontal, quench-cooled, stirred bed reactor.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

| | | | | | |
|----|--------------------------|----|---------------------------------------|----|--------------------------|
| AT | Austria | FR | France | MR | Mauritania |
| AU | Australia | GA | Gabon | MW | Malawi |
| BB | Barbados | GB | United Kingdom | NL | Netherlands |
| BE | Belgium | GN | Guinea | NO | Norway |
| BF | Burkina Faso | GR | Greece | NZ | New Zealand |
| BG | Bulgaria | HU | Hungary | PL | Poland |
| BJ | Benin | IR | Ireland | PT | Portugal |
| BR | Brazil | IT | Italy | RO | Romania |
| CA | Canada | JP | Japan | RU | Russian Federation |
| CF | Central African Republic | KP | Democratic People's Republic of Korea | SD | Sudan |
| CG | Congo | KR | Republic of Korea | SE | Sweden |
| CH | Switzerland | KZ | Kazakhstan | SK | Slovak Republic |
| CI | Côte d'Ivoire | LJ | Liechtenstein | SN | Senegal |
| CM | Cameroon | LK | Sri Lanka | SU | Soviet Union |
| CS | Czechoslovakia | LU | Luxembourg | TD | Chad |
| CZ | Czech Republic | MC | Monaco | TG | Togo |
| DE | Germany | MG | Madagascar | UA | Ukraine |
| DK | Denmark | ML | Mali | US | United States of America |
| ES | Spain | MN | Mongolia | VN | Viet Nam |
| FI | Finland | | | | |

POLYMERIZATION OF ALPHA-OLEFINS

BACKGROUND OF THE INVENTION

Field of the Invention

5 This invention relates generally to a process for the continuous polymerization of an alpha-olefin in the vapor phase in a substantially horizontal, quench-cooled, stirred-bed reactor, and more particularly relates to the control of the aforesaid process to produce a solid polymer having predetermined properties.

10 Discussion of the Prior Art

Shepard et al., U. S. Patent No. 3,957,448; Jezl et al., U.S. Patent No. 3,965,083; Jezl et al., U.S. Patent No. 3,970,611; Peters et al., U.S. Patent No. 3,971,768; Stasi, U.S. Patent No. 4,021,024; Jezl et al., U.S. Patent No. 4,101,289; Jezl et al., U.S. Patent No. 4,129,701; and Kreider et al., U.S. Patent No. 15 4,640,963, disclose various specific embodiments of a general method performed in a substantially horizontal reactor for the vapor-phase polymerization of at least one alpha-olefin monomer in a reaction mixture comprising a first alpha-olefin monomer and, if copolymerization is occurring, a second alpha-olefin monomer. The general method disclosed 20 comprises: conducting the polymerization under polymerization conditions of temperature and pressure in the presence of hydrogen and a catalyst system comprising a solid catalyst comprising a first metal and a cocatalyst comprising a second metal in a reactor wherein at least a portion of the heat of polymerization is removed by evaporative cooling of a readily 25 volatilizable quench liquid, and wherein the reactor comprises a substantially horizontal reactor of substantially circular cross-section containing a centrally-located drive shaft extending longitudinally through said reactor to which are attached a plurality of adjacently located paddles, which paddles cause essentially no forward or backward movement of the 30 particulate homopolymer or copolymer product contained in the reactor and extend transversely within and to a short distance from the internal surfaces of the reactor; driving means for the drive shaft; one or more reactor off-gas outlets spaced along the topward part of the reactor; a plurality of vapor recycle inlets spaced along the bottomward part of the reactor; one or more 35 catalyst and cocatalyst addition inlets spaced along the reactor; a plurality of quench liquid inlets spaced along the topward part of the reactor whereby

- 2 -

quench liquid can be introduced into the reactor; and take-off means for the particulate polymer product at one or both ends of the reactor.

In the preparation of solid polymers from alpha-olefins in a gas-phase polymerization in the aforesaid substantially horizontal, quench-cooled stirred-bed reactor, it would be highly desirable to control the polymerization reaction so as to provide a polymer product having predetermined and constant properties. In addition, a great deal of off-specification polymer product is produced during a transition period during which the polymerization conditions are changed from those employed in the manufacture of one grade of a polymer having one set of properties to those employed in the manufacture of another grade of the same polymer having a different set of properties or from those employed in the manufacture of homopolymer to those employed in the manufacture of a copolymer or vice versa.

In the operation of the aforesaid substantially horizontal, quench-cooled stirred bed polymerization reactor unit, there are a number of process changes that can lead to a situation where the process variables and product properties change with time. Several of these transient situations are operator induced while others are inherent to the process or caused by circumstances beyond the process operator's control. Among those situations controlled by the operator are: shut-down, start-up, production rate changes, and product grade changes. Grade changes tend to be very complex and time consuming. The main reason for the unusual complexity is that each grade change requires by definition that the plant's steady-state operating conditions be substantially disturbed. Furthermore, the problem is aggravated by the fact that during the transition several operating variables can change simultaneously. For example, some variables, like reactor temperature, pressure and catalyst feed, control the reaction rate, whereas others, such as hydrogen and/or propylene partial pressures, control the transition's speed and the ultimate polymer properties. Grade changes are always coupled with cost penalties due to the generation of off-specification material during the product transition.

Thus, in order to quantify the cost penalties associated with product transitions, it would be highly desirable to develop a mathematical model of the process. A critical utilization of this process model is in the form of an advanced control method that can be utilized for on-line minimization of grade transition times and to maintain safe operation from one product transition to another. It would also be desirable to reduce this transition

- 3 -

period and the amount of off-specification polymer produced during the transition period. Thus far, no method has been disclosed for controlling the continuous vapor-phase polymerization in the aforesaid substantially horizontal, quench-cooled, stirred-bed reactor.

5 The desired control of the polymerization process is extremely difficult to attain because of the holdup time of polymerization reactors and the time involved in obtaining polymer samples and measuring the properties of those samples. Because of this time period, the polymerization conditions employed in the reactor at the time at which a property of a
10 polymer sample withdrawn from the reactor is measured are not necessarily the same as the polymerization conditions employed in the reactor at the time at which such polymer sample was produced in the reactor and/or withdrawn from the reactor. This is especially the case when the attempted control of the polymerization process is based on the measurement of the
15 melt flow rate—or in other words, the melt index—of the polymer product as determined according to the ASTM Test D-1238-62T. Although the melt flow rate or the melt index is a satisfactory control property for most solid polymers prepared from alpha-olefins, the time consumed in obtaining a polymer sample for measurement and in measuring the melt index of the
20 sample, combines with the aforesaid holdup time of the reactor to seriously hamper accurate control of the polymerization process.

Consequently, it is highly desirable to develop an advanced on-line control method for the continuous gas-phase polymerization of alpha-olefins in the aforesaid substantially horizontal, quench-cooled, stirred-bed
25 reactor, which is based on measurements in real time of polymerization conditions in the reactor at the same time the control is being implemented. Such control methods have been disclosed for use in liquid phase polymerization reactor systems. For example, Smith et al., U.S. Patent No. 3,356,667 discloses a method and apparatus for controlling reaction
30 conditions of an alpha-olefin polymerization in the liquid phase in order to produce a solid polymer having specific properties. In addition to the basic reactor system, the apparatus disclosed as being useful in the practice of the disclosed method includes: means for feeding catalyst and reactant materials to the reactor system, means for withdrawing an effluent product stream
35 from the reactor system, means for removing reaction heat from the reactor system, computing means for establishing an output control signal representative of the instantaneous melt index of the polymer being produced in the reaction mixture, a second output signal representative of

the averaged melt index of the polymer in the effluent product stream removed from the reactor system, a third output signal representative of the average percent hydrogen in the reaction mixture within the reactor, and means for applying the output signal representative of the instantaneous
5 polymer melt index to control the rate of hydrogen addition to the reactor system so as to yield a polymer product having a predetermined melt index based on a predetermined concentration of hydrogen in the reaction zone. Also disclosed are computing means for establishing an output signal representative of polymer production rate and associated means for
10 controlling the rate of addition of catalyst to the reactor in response to the computed production rate.

Smith et al., U.S. Patent No. 3,356,667 also discloses that both the instantaneous melt index value of the polymer in the reaction zone and the melt index value of the polymer in the effluent from the reactor can be
15 determined by automatically computing these melt index values from the input data of various process variables of the reaction system. The computer inputs include (1) concentration of hydrogen in the monomer feed, (2) polymer concentration (percent solids) in the reactor system, (3) temperature of the reaction mixture, (4) rate of flow of the monomer to the reactor, and
20 (5) a time factor to compensate for delay. The production rate is also disclosed as a useful input signal. Thus, regulation of the hydrogen feed rate is accomplished in response to a hydrogen analysis in the feed corrected to indicate the hydrogen concentration in the liquid phase in the reactor. In addition, output signals representative of the melt index of the polymer in
25 the reactor effluent and the concentration of hydrogen in the reaction liquid are obtained.

The control system disclosed in the aforesaid U.S. Patent No. 3,356,667 employs as a basic unit thereof a computer which is adapted to receive input signals representative of the flow rate of propylene fed to the reactor system,
30 the hydrogen concentration in the propylene feed, the temperature of the reaction liquid in the reactor, and the percent solids (percent polymer) in the reaction mixture in the reactor. The signal representative of the flow rate of propylene, the signal representative of the hydrogen concentration, the signal representative of the temperature of the reaction contents in the
35 reactor, the signal representative of the polymer concentration (percent solids), and the signal representative of production rate are transmitted to the computer. The computer accepts the input signals from the primary measurement devices and produces three principal output signals that are

- 5 -

linearly proportional to the following process variables: (1) an output signal representing the concentration of hydrogen in the reaction liquid phase; (2) an output signal representing the instantaneous melt index of the polymer presently being produced in the reactor reaction mixture and (3) an output signal representing the integrated melt index of the polymer in the effluent stream removed from the reactor. The computer automatically combines the input signal to produce control output signals that are proportional to the instantaneous melt index, the concentration of hydrogen in the reaction liquid phase, and the melt index of the polymer in the reaction effluent and that are in response to the input signals.

A first control output signal proportional to the melt index of the polymer being produced at any instant within the reactor (instantaneous melt index) is transmitted to a melt index-recording-controller. The computed instantaneous melt index is compared by the controller with a predetermined desired polymer melt index value (set point), and a signal representative of this comparison is transmitted to manipulate the set point of an analyzer-recorder-controller. By so operating, in the method disclosed in the aforesaid U.S. Patent No. 3,356,667, the concentration of hydrogen in the reactor is maintained at a value capable of producing a polymer product having a predetermined melt index.

Furthermore, Smith, U.S. Patent No. 3,614,682 discloses a method for the digital computer control of a polymerization process that is performed in a continuously operating series of stirred reactors wherein each reactor continuously receives discharge of the preceding reactor in the series and continuously discharges into the succeeding reactor in the series. It is disclosed that at stated intervals, a computer begins a cycle, the first portion of which is a simulation routine whereby changes, since the last simulation, in important variables which take place at various points in the successive reactors in the train of reactors and which cannot be directly measured are followed by periodically numerically integrating by a digital computer for each reactor and for each of the variables, the equation

$$\frac{dX_i}{dt} = \frac{F}{V} (X_{i,n-1} - X_{i,n}) + \left(\frac{\delta X_{i,n}}{\delta t} \right)$$

wherein, in the terms employed in U.S. Patent No. 3,614,682, X is a process variable like concentration, conversion, etc., i is the first subscript of X and signifies that this is the ith of i variables, n is the second subscript of X and

- 6 -

signifies that this is the value of this variable in the nth one of the reactors in the train of reactors, F is the total volumetric flow rate, V is the volume of the nth reactor, t is the time under the reaction conditions, and $\delta X_{i,n}/\delta t$ is the overall rate of generation or degeneration of X under the conditions in the nth reactor. The resulting calculated values of these variables, together with directly measured values of other variables, are then manipulated by the computer and used to adjust the rate of feed of reagents and other conditions of polymerization in the train of reactors.

10

OBJECTS OF THE INVENTION

It is therefore a general object of the present invention to provide an improved method and control for the continuous, gas-phase polymerization of an alpha-olefin in a substantially horizontal, quench-cooled, stirred-bed reactor to produce solid polymer product having pre-determined properties.

15

More particularly, it is an object of the present invention to provide a method for the advanced control of the aforesaid polymerization to produce a polymer product having a pre-determined melt flow rate.

20

It is a further object of the present invention to provide a method for the advanced control of the aforesaid polymerization to produce a copolymer product of a first monomer and a second monomer having a predetermined content of the second monomer.

25

It is a further object of the present invention to provide an improved aforesaid advanced control method of the aforesaid polymerization under both steady state and transition conditions.

It is another object of the present invention to provide an improved aforesaid advanced control method of the aforesaid polymerization for the manufacture of homopolymers, random copolymers and impact copolymers.

30

Other objects and advantages of the present invention will become apparent upon reading the following detailed description and appended claims.

SUMMARY OF THE INVENTION

35

These objects are achieved by the method of this invention for the vapor-phase polymerization of at least one alpha-olefin monomer in a reaction mixture comprising a first alpha-olefin monomer and, if copolymerization is occurring, a second alpha-olefin monomer, comprising:

conducting the polymerization under polymerization conditions of temperature and pressure in the presence of hydrogen and a catalyst system comprising a solid catalyst comprising a first metal and a cocatalyst comprising a second metal, in at least one reactor wherein in each such reactor at least a portion of the heat of polymerization is removed by evaporative cooling of a volatilizable quench liquid comprising liquefied first monomer and, if copolymerization is occurring, liquefied second monomer and wherein each reactor is a substantially horizontal reactor of substantially circular cross-section containing a centrally-located drive shaft extending longitudinally through such reactor to which are attached a plurality of adjacently located paddles, which paddles cause essentially no forward or backward movement of the particulate polymer product contained in such reactor and extend transversely within and to a short distance from the internal surfaces of such reactor; driving means in each such reactor for the drive shaft; one or more reactor off-gas outlets spaced along the topward part of each such reactor; a plurality of vapor recycle inlets spaced along the bottomward part of each such reactor for recycle of unreacted first monomer and, if copolymerization is occurring, unreacted second monomer; one or more catalyst and cocatalyst addition inlets spaced along each such reactor; a plurality of quench liquid inlets spaced along the topward part of each such reactor whereby quench liquid can be introduced into such reactor; and take-off means in each such reactor for said particulate polymer product at one or both ends of such reactor.

In the method of the presentation invention, the performance of the aforesaid polymerization reaction is controlled in order to afford the production in each such reactor of a particulate polymer product having predetermined characteristics of at least one of the melt flow rate thereof and weight percent therein of the second monomer, if any, by a method comprising, for each reactor employed: (a₁) determining relationships between the melt flow rate of the particulate polymer product withdrawn from such reactor and a first set of parameters comprising the rates of introduction of quench liquid and vapor recycle into each zone of such reactor, the heat of polymerization in such reactor, the latent heat of vaporization of the quench liquid in such reactor, the total mass inventory of particulate product in such reactor and, the fraction in each zone of such reactor of the aforesaid total mass inventory in such reactor, the mole ratio of hydrogen to the first monomer in the vapor phase in such reactor, the mole ratio of the second monomer to the first monomer in the vapor phase

- 8 -

in such reactor, the mole ratio of the aforesaid second metal to the aforesaid first metal introduced into such reactor, the molecular weights of the first and second monomers, and the temperature and pressure in such reactor; (b₁) monitoring such first set of parameters; (c₁) from the first set of parameters monitored in step (b₁) and the relationships from step (a₁), calculating the melt flow rate of the polymer withdrawn from such reactor and (d₁) adjusting at least one of the reactor operating variables within minimum and maximum constraints thereof to adjust the calculated melt flow rate of the polymer withdrawn from such reactor to a pre-determined, set point level therefor, wherein such reactor variables are the mole ratio of the second monomer to the first monomer, if copolymerization is occurring, in the vapor phase in such reactor in the range of from about 0.0005 to about 0.5, the mole ratio of hydrogen to the first monomer in the vapor phase in such reactor in the range of from about 0.0005 to about 0.08, the mole ratio of the second metal to the first metal introduced into such reactor in the range of from about 14 to about 200, the rate of introduction of the quench liquid into each zone of such reactor in the range of from about 5 to about 50 kg/sec, the ratio of the rate of introduction of the vapor recycle to the rate of introduction of quench liquid into each zone of such reactor in the range of from about 0.05 to about 0.3, and the temperature in such reactor in the range of from about 20°C to about 100°C.

BRIEF DESCRIPTION OF THE DRAWINGS

For a more complete understanding of the present invention, reference should now be made to the embodiments illustrated in greater detail in the accompanying drawings and described below by way of examples of the invention. In the drawings:

FIGURE 1 is a schematic drawing of the single substantially horizontal, quench-cooled, stirred bed reactor and associated equipment as employed in the method of this invention for the polymerization of propylene to form polypropylene or for the copolymerization of propylene and ethylene to form a copolymer of propylene and ethylene; and

FIGURE 2 is a plot of the calculated melt flow rates of polypropylene withdrawn from a reactor versus the time during the transition when the mole ratio of hydrogen to propylene is first increased from that level therefor at which a polypropylene product that has a melt flow rate of 3 is produced at steady state to that level therefor at which a polypropylene product that has a melt flow rate of 10 is produced at steady state.

- 9 -

It should be understood that in certain instances, details which are not necessary for an understanding of the present invention or which render other details difficult to perceive may have been omitted. It should be understood, of course, that the invention is not necessarily limited to be
5 particular embodiments illustrated herein.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention is a method for controlling the continuous gas-phase polymerization of an alpha-olefin in a substantially horizontal, quench-cooled stirred-bed reactor, various specific embodiments of which
10 are disclosed in Shepard et al., U.S. Patent No. 3,957,448; Jezl et al., U.S. Patent No. 3,965,083; Jezl et al., U.S. Patent No. 3,970,611; Peters et al., U.S. Patent No. 3,971,768; Stasi, U.S. Patent No. 4,021,024; Jezl et al., U.S. Patent No. 4,101,289; Jezl et al., U.S. Patent No. 4,129,701; and Kreider et al., U.S.
15 Patent No. 4,640,963, each of which in its entirety is specifically incorporated herein by reference.

The method of the present invention is employed with at least one substantially horizontal reactor of substantially circular cross-section containing a centrally-located drive shaft extending longitudinally through
20 each such reactor, to which are attached a plurality of adjacently located paddles, which paddles cause essentially no forward or backward movement of the particulate polymer product contained in such reactor and extend transversely within and to a short distance from the internal surfaces of such reactor; driving means in each such reactor for the drive shaft; one or
25 more reactor off-gas outlets spaced along the topward part of each such reactor; a plurality of vapor recycle inlets spaced along the bottomward part of the reactor; one or more catalyst and cocatalyst addition inlets spaced along each such reactor; a plurality of quench liquid inlets spaced along the topward part of each such reactor whereby quench liquid can be introduced
30 into each such reactor; and take-off means in each such reactor for the particulate product at one or both ends, preferably at one end of such reactor.

The polymerization process using a single aforesaid substantially horizontal reactor for manufacturing a homopolymer, for example, of propylene, and a random copolymer, for example, of propylene and ethylene
35 is shown schematically in Figure 1. In Figure 1, the vessel where the polymerization occurs is a horizontal cylindrical reactor 10 that contains, for example, polypropylene powder 12, agitated by a series of flat paddles 14 attached to a center shaft 16. The reactor 10 operates under an internal

- 10 -

pressure of about 200-400 psig and at a temperature of about 50-90°C. The powder level in the reactor 10 is maintained at approximately 40-60 percent of the total reactor level while the catalyst and cocatalyst are fed into the reactor 10 through one of more possible locations 18 and 20. Optionally, a
5 modifier such as a silane modifier is also introduced in a single stream into the top of the reactor 10 through one or more possible locations. The reactor temperature is mainly controlled by means of a recycle liquid propylene which is sprayed at several axial locations 22 onto the bed. The propylene quench liquid is vaporized after absorbing the heat of the polymerization
10 reaction. Recycle gas is returned to the bottom of the reactor 10 at a number of inlets 24. Make-up hydrogen is introduced into the suction of the recycle gas compressor (not shown) for melt flow rate adjustment.

The vaporized propylene exits the reactor through two large domes 26 that are connected to the top of the reactor 10. The domes 26 are designed to
15 allow only small particles (fines) to exit the reactor 10. The gases and the entrained polymer fines are fed to a cyclone 28. The fines that are removed from the gas are then returned to the top of the reactor 10 as close to the front as possible by means of a fines' recycle ejector 30. The gas is sent to a condenser 32.

20 The reactor off-gas is then partially condensed in a horizontal condenser 32. The gas and liquid from the condenser 32 are separated in the overhead separator drum 34. Part of the recycle gas is vented on flow control to remove the propane accumulated in the system. In this manner a constant propylene partial pressure is kept in the reactor vapor space. The
25 remaining gas is slightly superheated in the recycle gas heater (not shown) to prevent condensation before it is mixed with hydrogen and compressed in the recycle gas compressor (not shown). The majority of the stream from the discharge of the recycle gas compressor is returned to the reactor 10, while a small amount is sent to the reactor fines' recycle ejector 30 that
30 returns the fines removed from the cyclone 28. Fresh polymer grade propylene feed containing small amounts of propane impurities is fed to the overhead separator drum 34. The quench liquid is returned to the reactor 10 by means of a pump (not shown) that provides a constant pressure at the quench liquid nozzle inlets 22, so that the liquid spray pattern remains the
35 same. Polypropylene powder is discharged periodically from the reactor 10, on time control, to a gas expansion bag filter (not shown).

In the manufacture of random copolymers, an ethylene gas stream is introduced into the overhead reactor separator drum 34 as can be seen in

- 11 -

Figure 1. The ethylene gas is carried with the propylene gas that returns to the reactor 10 by means of the recycle gas compressor. Some ethylene will leave the reactor 10 with the gas that is vented to remove the accumulated impurities (propane and ethane). The random copolymer powder is discharged from the reactor, on time control, to a gas expansion bag filter (not shown).

For the purpose of this invention, the aforesaid substantially horizontal, quench cooled stirred bed reactor employed in the method of this invention is viewed as a series of zones whereby, each such zone is characterized during non-steady state operation, in that polymer product particles therein have uniform properties and is preceded and succeeded by adjacent zones of similarly uniform properties but different from the zone in question. Thus, a given property of the particulate polymer product is the same within a zone but changes from one zone to the next. Thus, the zones are treated as continuous stirred tank reactors in accordance with the approach discussed in detail in Chapter 9 entitled "Nonideal Flow" on page 253-325 in O. Levenspiel, Chemical Reaction Engineering, John Wiley & Sons, New York, 1972. The number of zones in an aforesaid substantially horizontal reactor employed in the method of this invention is determined in accordance with the methods and calculations in pages 290-304 of Levenspiel.

As employed herein, unless otherwise indicated, the term "polymerization" is intended to include both homopolymerization and copolymerization, and the term "polymer" is intended to include both homopolymer and copolymer.

The method of this invention is useful in the stereospecific polymerization of alpha-olefins containing 3 or more carbon atoms such as propylene, butene-1, pentene-1, 4-methylpentene-1, and hexene-1, as well as mixtures thereof and mixtures thereof with ethylene. The method of this invention is particularly effective in the stereospecific polymerization of propylene or mixtures thereof with ethylene or a higher alpha-olefin. According to the invention, highly crystalline polyalpha-olefin homopolymers or copolymers are prepared by contacting at least one alpha-olefin with the catalyst described hereinbelow under polymerization conditions. Such conditions include polymerization temperature and time, pressure(s) of the monomer(s), avoidance of contamination of catalyst, the use of chain transfer agents to control polymer molecular weights, and other conditions well known to persons skilled in the art.

- 12 -

In the method of the present invention, polymerization should be carried out at temperatures sufficiently high to ensure reasonable polymerization rates and to avoid unduly long reactor residence times, but not so high as to result in the production of unreasonably high levels of stereorandom products due to excessively rapid polymerization rates. Generally, temperatures range from about 0° to about 120°C, with a range of from about 20°C to about 95°C being preferred from the standpoint of attaining good catalyst performance and high production rates. More preferably, polymerization according to this invention is carried out at temperatures ranging from about 50°C to about 80°C.

Alpha-olefin polymerization according to this invention is carried out at monomer pressures of about atmospheric or above. Monomer pressures should not be below the vapor pressure at the polymerization temperature of the alpha-olefin to be polymerized, and generally monomer pressures range from about 20 to about 600 psi.

The amount of the catalyst or catalyst component to be employed in the method of this invention varies depending on choice of reactor size, monomer to be polymerized, the specific catalyst used, and other factors known to persons of skill in the art. Typically, a catalyst or catalyst component is used in amounts ranging from about 0.2 to 0.02 milligrams of catalyst to gram of polymer produced.

The Ziegler catalysts to be used in the preparation of polyolefins according to the present invention generally contain two major components: (a) a compound of a transition metal belonging to Group IV to VI in the Mendelejeff's periodic table, and (b) an organometallic compound or hydride of a metal belonging to Group I to III in the periodic table. Especially preferred are those that contain as the major constituent a titanium or vanadium halide, and an organoaluminum compound. The components (a) and (b) may be supported on a carrier or may be denatured with a denaturing agent such as an electron donor. As the Ziegler catalysts in the present invention, there may be employed those disclosed, for example, in U.S. Patent Nos. 3,257,332; 3,826,792; 3,113,115; 3,546,133; 4,125,698; 4,071,672; 4,071,674; 3,642,746; 3,051,690 and 3,058,963, and British Patent No. 1,140,649.

While a wide variety of organometallic systems or solid catalysts can be employed for the polymerization of olefins, particularly propylene, to solid polymers, it is often preferred to use a catalyst which includes a combination of an aluminum alkyl and a titanium halide, preferably a

- 13 -

dialkyl aluminum chloride or bromide, including mixtures of the two halides, in which the alkyl groups have from 1 to 12 carbon atoms each and a titanium chloride. The catalyst system most preferred is a mixture of diethylaluminum chloride and a titanium chloride complex. The titanium chloride complex is preferably an aluminum-reduced titanium tetrachloride formed by reacting aluminum with titanium tetrachloride. The preferred aluminum-reduced TiCl_4 can be described as being of the composition $\text{TiCl}_3 \cdot \chi \text{AlCl}_3$ in which χ is a number in the range of 0.1 to 1.0. A convenient method for the preparation of such a material is by reduction of titanium tetrachloride with metallic aluminum according to the formula $3\text{TiCl}_4 + \text{Al}$. This reaction is generally carried out at an elevated temperature, for example, a temperature in the range 300 to 650°F., preferably 375° to 450°F.

In general, the catalysts which are most useful to the process described herein are those which are very active and give a high yield on catalyst. Included in this group are cocatalysts composed of organometallic compounds of Periodic Groups IA, IIA and IIIA and catalysts which are based on transition metal compounds. Aluminum alkyl compound cocatalysts are especially preferred and may be a trialkylaluminum or an alkylaluminum halide such as a dialkylaluminum chloride. The transition metal catalyst can be a metal compound of Group IV or Group V such as a titanium or vanadium compound, a compound of Group VI such as chromium or molybdenum oxide or may be one of the above catalysts supported on a magnesium-based support or a support such as alumina, silica, or silica-alumina. The preferred catalysts and cocatalysts are the aforesaid high yield catalysts. By high yield is meant catalysts and cocatalysts the residues of which do not have to be removed from the products of the polymerization process.

More particularly, the catalyst system employed herein comprises the catalyst or catalyst component described hereinbelow and a cocatalyst component comprising a Group IIA or IIIA metal alkyl. Group IIA and IIIA metal alkyls that are suitable for use as such cocatalyst component are compounds of the formula MR_m wherein M is a Group IIA or IIIA metal, each R is independently an alkyl radical of 1 to about 20 carbon atoms, and m corresponds to the valence of M. Examples of useful metals, M, include magnesium, calcium, zinc, cadmium, aluminum, and gallium. Examples of suitable alkyl radicals, R, include methyl, ethyl, butyl, hexyl, decyl, tetradecyl, and eicosyl. From the standpoint of catalyst component performance, preferred Group IIA and IIIA metal alkyls are those of magnesium, zinc, or

- 14 -

aluminum wherein the alkyl radicals contain 1 to about 12 carbon atoms. Specific examples of such compounds include $\text{Mg}(\text{CH}_3)_2$, $\text{Mg}(\text{C}_2\text{H}_5)_2$, $\text{Mg}(\text{C}_2\text{H}_5)(\text{C}_4\text{H}_9)$, $\text{Mg}(\text{C}_4\text{H}_9)_2$, $\text{Mg}(\text{C}_6\text{H}_{13})_2$, $\text{Mg}(\text{C}_{12}\text{H}_{25})_2$, $\text{Zn}(\text{CH}_3)_2$, $\text{Zn}(\text{C}_2\text{H}_5)_2$, $\text{Zn}(\text{C}_4\text{H}_9)_2$, $\text{Zn}(\text{C}_4\text{H}_9)(\text{C}_8\text{H}_{17})$, $\text{Zn}(\text{C}_6\text{H}_{13})_2$, $\text{Zn}(\text{C}_6\text{H}_{13})_3$, and $\text{Al}(\text{C}_{12}\text{H}_{25})_3$.

- 5 More preferably a magnesium, zinc, or aluminum alkyl containing 1 to about 6 carbon atoms per alkyl radical is used. Best results are achieved through the use of trialkylaluminums containing from 1 to about 6 carbon atoms per alkyl radical, and particularly trimethylaluminum, triethylaluminum and triisobutylaluminum, or a combination thereof. If
10 desired, metal alkyls having one or more halogen or hydride groups can be employed, such as ethylaluminum dichloride, diethylaluminum chloride, ethylaluminum sesquichloride, diethylaluminum hydride, diisobutylaluminum hydride, and the like.

- In addition to the catalyst or catalyst component described
15 hereinbelow and aforesaid cocatalyst component, the catalyst system employed in the method of the present invention typically includes an aliphatic or aromatic organosilane compound. A suitable class of organosilane comprises either (1) $\text{R}_1(\text{R}_2)_x\text{Si}(\text{OR}_4)_y(\text{OR}_5)_z$ wherein R_1 and R_2
20 are the same or different and are each isopropyl, isobutyl, sec-butyl, t-butyl, isopentyl, t-pentyl, neopentyl, phenyl, tolyl, naphthyl, or cyclo $\text{C}(\text{R}_3)_{2n-1}$, wherein cycloC is a cyclobutyl, cyclopentyl or cyclohexyl cycloaliphatic ring attached to the silicon atom and R_3 is hydrogen or an alkyl group having
from 1 to 5 carbon atoms and is a substituent to the cycloaliphatic ring, and wherein n is 4, 5 or 6 when the cycloaliphatic ring is cyclobutyl, cyclopentyl
25 or cyclohexyl, respectively, wherein R_4 and R_5 are the same or different and are each methyl, isopropyl, or sec- or t-butyl, and, wherein y is 1, 2 or 3, z is 0 or 1, y+z is 2 or 3, and x is 3-(y+z). Preferably, z is 0, y is 2, R_4 is methyl or t-butyl, x is 1 and R_1 and R_2 are the both isopropyl, isobutyl, t-butyl, isopentyl, t-pentyl, or neopentyl. Typically, the silane employed as an external
30 modifier in the method of this invention is diisopropyldimethoxysilane, diisobutyldimethoxysilane, di-t-butyldimethoxysilane, t-butyltrimethoxysilane, diisopentyldimethoxysilane, di-t-pentyldimethoxysilane, dineopentyl- dimethoxysilane, neopentyltrimethoxysilane, isobutylisopropyl- dimethoxysilane, isobutyl-t-butyl
35 butyldimethoxysilane, and iso-propyl-t-butyldimethoxysilane and di-p-tolyldimethoxysilane. Preferably, the silane employed as an external modifier is diisopropyldimethoxysilane or di-t-butyldimethoxysilane.

- 15 -

The aforesaid silane is present in the catalyst system employed in the method of this invention at a molar ratio of the metal in the cocatalyst to silane in the range of from about 1, preferably from about 3, to about 50, preferably to about 30.

5 Thus, a typical catalyst system for the polymerization or copolymerization of alpha-olefins by the method of this invention is formed by combining the supported titanium-containing catalyst or catalyst component described hereinbelow and an aforesaid alkyl aluminum compound as catalysts, together with the aforesaid silane. Typically, useful
10 aluminum-to-titanium atomic ratios in such catalyst systems are about 10 to about 500 and preferably about 30 to about 400. Typical aluminum-to-silane compound molar ratios in such catalyst systems are about 3 to about 30.

 Titanium-containing catalyst components that are especially useful in this invention are supported on hydrocarbon-insoluble, magnesium-
15 containing compounds which are optionally in combination with an electron donor compound as an internal modifier. Such supported titanium-containing olefin polymerization catalyst component typically is formed by reacting a titanium (IV) halide, a magnesium-containing compound, and optionally an organic electron donor compound.
20 Optionally, as described hereinbelow, such supported titanium-containing reaction product may be further treated or modified by comminution or further chemical treatment with additional electron donor or Lewis acid species.

 Suitable magnesium-containing compounds include magnesium
25 halides; a reaction product of a magnesium halide such as magnesium chloride or magnesium bromide with an organic compound, such as an alcohol or an organic acid ester, or with an organometallic compound of metals of Groups I-III; magnesium alcoholates; or magnesium alkyls.

 One possible magnesium-containing compound, described in U.S.
30 Patent No. 4,277,370, is based on at least one magnesium alcoholate which may be pretreated with at least one modifier such as a mineral acid or anhydride of sulfur, organometallic, chalcogenide derivative of hydrogen sulfide, and organic acids and esters thereof. Such magnesium-containing compound may be the pretreatment product of at least one magnesium
35 alcoholate, at least one Group II or IIIA metal alkyl and, optionally, at least one modifier such as a mineral acid or an anhydride, sulfur, organometallic chalcogenide derivatives of hydrogen sulfide, organic acids and organic acid esters. Solid magnesium alkoxide may be milled prior to further treatment.

- 16 -

In another catalyst component, magnesium ethoxide may be reacted with an aromatic ester such as phenyl benzoate prior to further treatment with a Lewis acid.

Another possible catalyst component is described in U.S. application
5 Serial No. 674,966, filed December 26, 1984, assigned to a common assignee,
which is incorporated by reference herein. The catalyst component described
therein is prepared by complexing a magnesium alkyl composition with a
specific class of hindered aromatic ester such as ethyl 2,6-dimethylbenzoate
followed by reaction with a compatible precipitation agent such as silicon
10 tetrachloride and a suitable titanium (IV) compound in combination with
an organic electron donor compound in a suitable diluent.

Another possible, and preferable, catalyst component is described in
U.S. Serial No. 875,180, filed June 17, 1986, which is a continuation-in-part to
U.S. application Serial No. 741,858, filed June 6, 1985, which was a
15 continuation-in-part to U.S. application Serial Nos. 629,910, filed July 9, 1984,
and 592,910, filed March 23, 1984, now the above-described U.S. Patent No.
4,540,679, all of which are assigned to a common assignee and are
incorporated by reference herein.

The possible solid catalyst components listed above are only
20 illustrative of many possible solid, magnesium-containing, titanium halide-
based, hydrocarbon-insoluble catalyst components useful in this invention
and known to the art. This invention is not limited to a specific supported
catalyst or catalyst component.

Titanium (IV) compounds useful in preparing the solid titanium-
25 containing catalyst component of invention are titanium halides and
haloalcoholates having 1 to about 20 carbon atoms per alcoholate group.
Mixtures of titanium compounds can be employed if desired. Preferred
titanium compounds are the halides and haloalcoholates having 1 to about
8 carbon atoms per alcoholate group. Examples of such compounds include
30 TiCl_4 , TiBr_4 , $\text{Ti}(\text{OCH}_3)\text{Cl}_3$, $\text{Ti}(\text{OC}_2\text{H}_5)\text{Cl}_3$, $\text{Ti}(\text{OC}_4\text{H}_9)\text{Cl}_3$, $\text{Ti}(\text{OC}_6\text{H}_5)\text{Cl}_3$,
 $\text{Ti}(\text{OC}_6\text{H}_{13})\text{Br}_3$, $\text{Ti}(\text{OC}_8\text{H}_{17})\text{Cl}_3$, $\text{Ti}(\text{OCH}_3)_2\text{Br}_2$, $\text{Ti}(\text{OC}_2\text{H}_5)\text{Cl}_2$,
 $\text{Ti}(\text{OCH}_6\text{H}_{13})_2\text{Cl}_2$, $\text{Ti}(\text{OC}_8\text{H}_{17})_2\text{Br}_2$, $\text{Ti}(\text{OCH}_3)_3\text{Br}$, $\text{Ti}(\text{OC}_2\text{H}_5)_3\text{Cl}$,
 $\text{Ti}(\text{OC}_4\text{H}_9)_3\text{Cl}$, $\text{Ti}(\text{OC}_6\text{H}_{13})_3\text{Br}$, and $\text{Ti}(\text{OC}_8\text{H}_{17})_3\text{Cl}$. Titanium tetrahalides,
particularly titanium tetrachloride (TiCl_4), are most preferred.

35 Organic electron donors useful as internal modifiers in preparation of
stereospecific supported titanium-containing catalyst components many
times can be organic compounds containing one or more atoms of oxygen,
nitrogen, sulfur, and phosphorus. Such compounds include organic acids,

- 17 -

organic acid esters, alcohols, ethers, aldehydes, ketones, amines, amine oxides, amides, thiols and various phosphorous acid esters and amides, and the like. Mixtures of organic electron donors can be used if desired. Specific examples of useful oxygen-containing electron donor compounds include
5 organic acids and esters. Useful organic acids contain from 1 to about 20 carbon atoms and 1 to about 4 carboxyl groups.

Preferred titanium component electron donor compounds as internal modifiers include esters of aromatic acids. Preferred organic electron donors are C₁-C₆ alkyl esters of aromatic mono- and dicarboxylic acids and halo-
10 gren-, hydroxyl-, oxo-, alkyl-, alkoxy-, aryl-, and aryloxy-substituted aromatic mono- and dicarboxylic acids. Among these, the alkyl esters of benzoic and halobenzoic acids wherein the alkyl group contains 1 to 6 carbon atoms, such as methyl benzoate, methyl bromobenzoate, ethyl benzoate, ethyl chlorobenzoate, ethyl bromobenzoate, butyl benzoate, isobutyl benzoate,
15 hexyl benzoate, and cyclohexyl benzoate, are preferred. Other preferable esters include ethyl p-anisate and methyl-p-toluate. An especially preferred aromatic ester is a dialkylphthalate ester in which the alkyl group contains from about two to about ten carbon atoms. Examples of preferred phthalate ester are diisobutylphthalate, ethylbutylphthalate, diethylphthalate, and di-
20 n-butylphthalate.

The electron donor component that may be used as internal modifiers in preparation of the solid catalyst component is used in an amount ranging from about 0.001 to about 1.0 mole per gram atom of titanium, and preferably from about 0.005 to about 0.9 mole per gram atom. Best results are
25 achieved when this ratio ranges from about 0.01 to about 0.8 mole per gram atom of titanium.

Although not required, the solid reaction product prepared as described herein may be contacted with at least one liquid Lewis acid prior to polymerization. Such Lewis acids useful according to this invention are
30 materials which are liquid at treatment temperatures and have a Lewis acidity high enough to remove impurities such as unreacted starting materials and poorly affixed compounds from the surface of the above-described solid reaction product. Preferred Lewis acids include halides of Group III-V metals which are in the liquid state at temperatures up to about
35 170°C. Specific examples of such materials include BCl₃, AlBr₃, TiCl₄, TiBr₄, SiCl₄, GeCl₄, SnCl₄, PCl₃ and SbCl₅. Preferable Lewis acids are TiCl₄ and SiCl₄. Mixtures of Lewis acids can be employed if desired. Such Lewis acid may be used in a compatible diluent.

- 18 -

The method of this invention for controlling the performance of the aforesaid polymerization reaction in order to afford the production of a particulate polymer product having predetermined characteristics of at least one of the melt flow rate thereof and the weight percent therein of the second monomer, if any, comprises, for each reactor employed:

(a₁) determining relationships between the melt flow rate of the particulate polymer product withdrawn from such reactor and a first set of parameters comprising the rates of introduction of quench liquid and vapor recycle into each zone of such reactor, the heat of polymerization in such reactor, the latent heat of vaporization of the quench liquid in such reactor, the total mass inventory of particulate polymer product in such reactor and the fraction in each zone of such reactor of the aforesaid total mass inventory in such reactor, the mole ratio of hydrogen to the first monomer, preferably propylene, in the vapor phase in such reactor, the mole ratio of the second monomer, preferably ethylene, to the first monomer, preferably propylene, in the vapor phase in such reactor, the mole ratio of the aforesaid second metal to the aforesaid first metal introduced into such reactor, the molecular weights of the first and second monomers, the relative reactivities of the first and second monomers in the formation of the copolymer if copolymerization occurs, and the temperature and pressure in such reactor; (b₁) monitoring such first set of parameters; (c₁) from the first set of parameters monitored in step (b₁) and the relationships from step (a₁), calculating the melt flow rate of the polymer withdrawn from such reactor; and (d₁) adjusting at least one of the reactor operating variables within minimum and maximum constraints thereof to adjust the calculated melt flow rate of the polymer withdrawn from such reactor to a pre-determined, set point level therefor, wherein such reactor variables are the mole ratio of the second monomer to the first monomer, if copolymerization is occurring, in the vapor phase in such reactor in the range of from about 0.0005 to about 0.5, preferably for random copolymers from about 0.004 to about 0.03, and preferably for impact copolymers from about 0.2 to about 0.4, the mole ratio of hydrogen to the first monomer in the vapor phase in such reactor in the range of from about 0.0005, preferably from about 0.002, to about 0.08, preferably to about 0.04, the mole ratio of the second metal to the first metal introduced into such reactor in the range of from about 14, preferably from about 60, to about 200, preferably to about 120, the rate of introduction of the quench liquid into each zone of such reactor in the range of from about 5 kg/sec, preferably from about 15 kg/sec, to about 50 kg/sec, preferably to

- 19 -

about 35 kg/sec, the ratio of the rate of introduction of the vapor recycle to the rate of introduction of quench liquid into each zone of such reactor in the range of from about 0.05, preferably from about 0.1, to about 0.3, preferably to about 0.2, and the temperature in each reactor in the range of
5 from about 20°C, preferably from about 50°C, to about 100°C, preferably to about 80°C.

Preferably, the method of the present invention additionally comprises, for each reactor employed: (a₂) determining relationships
10 between the weight percent of the second monomer in the particulate copolymer product, if copolymerization occurs, withdrawn from such reactor and a second set of parameters comprising the rates of introduction of quench liquid and vapor recycle into each zone of such reactor, the heat of polymerization in such reactor, the latent heat of vaporization of the quench liquid in such reactor, the total mass inventory of particulate product in
15 such reactor and the fraction in each zone of such reactor of the aforesaid total mass inventory in such reactor, the mole ratio of second monomer to the first monomer in the vapor phase in such reactor, the relative reactivities of the first and second monomer in the formation of the copolymer, and the molecular weights of the first and second monomers;
20 (b₂) monitoring such second set of parameters; (c₂) from the second set of parameters monitored in step (b₂) and the relationships from step (a₂), calculating the weight percent of the second monomer in the copolymer product withdrawn from such reactor; and (d₂) adjusting at least one of the reactor operating variables within minimum and maximum constraints
25 thereof to adjust the weight percent of second monomer in the copolymer withdrawn from such reactor to a pre-determined level therefor, wherein such reactor variables are the mole ratio of the second monomer to the first monomer in the vapor phase in such reactor in the range from about 0.0005 to about 0.5, preferably for random copolymers from about 0.004 to about
30 0.03, and preferably for impact copolymers from about 0.2 to about 0.4, the rate of introduction of the quench liquid into each zone of such reactor in the range of from about 5 kg/sec, preferably from about 15 kg/sec, to about 50 kg/sec, preferably to about 35 kg/sec, and the ratio of the rate of introduction of the vapor recycle to the rate of introduction of quench liquid into each
35 zone of such reactor in the range of from about 0.05, preferably from about 0.1, to about 0.3, preferably to about 0.2.

In its most preferred embodiment, the method of the present invention for controlling the performance of the aforesaid polymerization

- 20 -

reaction comprises, for each reactor employed: (a₃) determining the temperature and pressure in such reactor; (b₃) determining the mole ratios of

- 5 (1) hydrogen to the first monomer in the vapor phase in such reactor,
- (2) the second monomer to the first monomer in the vapor phase in such reactor, and
- (3) the aforesaid second metal to the aforesaid first metal introduced into such reactor;
- 10 (c₃) determining the rates in parts by weight per unit of time of the introduction of each of the quench liquid and the vapor recycle into each zone of such reactor; (d₃) determining the rate of production of the particulate polymer product in each zone of such reactor as follows:

$$15 \quad R_z = \frac{L_z(1 + G_z/L_z)}{1 + H_p/H_v} \quad (\text{Equation 1})$$

wherein the subscript Z is the number of the zone and ranges from 1 to N, R_z is the production rate of the particulate polymer product in zone Z, L_z is the rate of introduction of the quench liquid into zone Z, G_z is the rate of introduction of the vapor recycle into zone Z, H_p is the heat of polymerization in zone Z, and H_v is the latent heat of vaporization of the quench liquid in zone Z; (e₃) determining the mass inventory of particulate polymer product in each zone of such reactor from the fraction in each such zone of the total mass inventory of particulate polymer product in such reactor and the total mass inventory of particulate polymer product in such reactor, as follows:

$$W_z = f_z W \quad (\text{Equation 2})$$

wherein W is the aforesaid total mass inventory in such reactor, f_z is the aforesaid fraction in the zone Z in such reactor, and W_z is the aforesaid mass inventory in such zone Z; (f₃) determining the time constant for each zone of each reactor, as follows:

$$30 \quad \tau_z = \frac{W_z}{\sum_{z=1}^Z R_z} \quad (\text{Equation 3})$$

- 21 -

wherein τ_z is the time constant in zone Z;

(g₃) for the particulate polymer product being produced instantaneously within such reactor at any instant of steady-state or transition operation, determining at least one of the instantaneous melt flow rate thereof or the
5 instantaneous weight percent of the second monomer therein as follows:

$$I_n(MFR_i) = \alpha - \frac{\beta}{T} + \gamma \ln \left[\left(\frac{H_2}{I} \right) + \delta \left(\frac{M_2}{M_1} \right) \right] + \gamma \ln \left[\frac{(r_2 + r_3 \Pi/I) (MW_{II})}{r_2 (MW_{II}) + \Pi/I (MW_I) + (MW_{II}) + r_1 \Pi/I^2 (MW_I)} \right]$$

(Equation 4)

$$Wt.\% \Pi_i = 100 J \left[\frac{(r_1 (\Pi/I)^2 + (\Pi/I)) (MW_I)}{(r_1 (\Pi/I)^2 + (\Pi/I)) (MW_I) + (r_2 + (\Pi/I)) (MW_{II})} \right]$$

(Equation 5)

where MFR_i is the instantaneous melt flow rate of the polymer product being produced in such reactor at that instant, Wt.% Π_i is the instantaneous
15 weight percent of the second monomer, if any, in the polymer product being produced in such reactor at that instant, T is the temperature in degrees centigrade, H₂/I is the mole ratio of hydrogen to the first monomer in the vapor phase in such reactor, M₂/M₁ is the mole ratio of the aforesaid second metal to the aforesaid first metal introduced into such reactor, Π/I is the
20 mole ratio of the second monomer to the first of the first monomer, MW_{II} is the molecular weight of the second monomer, monomer in the vapor phase in such reactor, MW_I is the molecular weight of the first monomer, J is the fraction of an impact copolymer that is represented by the random copolymer component thereof, and α , β , γ , δ , r_1 , r_2 and r_3 are catalyst and
25 reactor system - dependent constants which are determined from experimental data;

(h₃) determining the value of X for the polymer product withdrawn from the last zone N of such reactor, as follows:

- 22 -

$$X_t^N = \left(\frac{\Delta t}{\tau_N + \Delta t} \right) \left[\left(\frac{R_N}{\sum_{z=1}^N R_z} \right) X_i + \left(\frac{\sum_{z=1}^{N-1} R_z}{\sum_{z=1}^N R_z} \right) X_t^{N-1} \right] + \left(\frac{\tau_N}{\tau_N + \Delta t} \right) X_{t-\Delta t}^N$$

(Equation 6)

wherein N is the number of the last zone in such reactor, N-1 is the number of the preceding zone, X_t^N is the value of the $\ln(\text{MFR}_t)$ or $\text{Wt.}\% \Pi_t$, from zone N at time t, Δt is the sampling time interval, X_i is the instantaneous value of the $\ln(\text{MFR}_i)$ or $\text{Wt.}\% \Pi_i$ determined in Equations 4 or 5, respectively, $X_{t-\Delta t}^N$ is the calculated value of X for the same zone N but for the immediately preceding sampling interval and X_t^{N-1} is the calculated value of X for the same sampling interval but for zone N-1;

(i₃) determining the difference between X_t^N for MFR_t^N or $\text{Wt.}\% \Pi_t^N$, calculated in Equation 6 and the predetermined set point value therefor and in response to the determined difference, adjusting

(1) at least one of the temperature, Π/I , H_2/I , M_2/M_1 , L_z , or G_z/L_z for MFR_t^N , or

(2) at least one of the Π/I , L_z , or G_z/L_z for $\text{Wt.}\% \Pi_t^N$;

in order to reduce the difference to a pre-determined acceptable level therefor.

When two reactors in series are employed, the zones for the first reactor are numbered starting with $Z = 1$ for zone 1, and the zones for the second reactor are numbered starting with the next integer after the number of the last zone in the first reactor. Thus, N is the number of the last zone in the last reactor in the series of reactors.

Equations 1-6 are applicable to systems involving the use either of one reactor for the polymerization of a single monomer, preferably propylene, to produce a homopolymer or for the polymerization of two monomers, preferably propylene and ethylene, to provide a copolymer, or of two reactors in series in which a first monomer, preferably propylene, is polymerized in the first reactor to produce a homopolymer which is then

transferred to a second reactor where a random copolymer is formed into the aforesaid homopolymer by copolymerization of the first monomer, preferably propylene with a second monomer, preferably ethylene, to afford an impact copolymer.

- 5 When only a single reactor is employed for the formation of either a homopolymer or a random copolymer, Equations 4 and 5 simplify to the following Equations 7 and 8, respectively:

$$\ln(\text{MFR}_i) = \alpha - \frac{\beta}{T} + \gamma \ln \left[\left(\frac{H_2}{I} \right) + \delta \left(\frac{M_2}{M_1} \right) \right] + \gamma \ln \left[\frac{r_2 (M W_{II})}{r_2 (M W_{II}) + (M/D) ((M W_I) + (M W_{II}))} \right]$$

10

(Equation 7)

$$\text{Wt. \% } \Pi_i = \frac{100 (M/D) (M W_I)}{r_2 (M W_{II}) + (M/D) ((M W_I) + (M W_{II}))}$$

(Equation 8)

- 15 When only a single reactor is employed for the formation of a homopolymer, Equation 7 simplifies to Equation 9:

$$\ln(\text{MFR}_i) = \alpha - \frac{\beta}{T} + \gamma \ln \left[\left(\frac{H_2}{I} \right) + \delta \left(\frac{M_2}{M_1} \right) \right]$$

(Equation 9)

20

- For the purpose of making the aforesaid calculations, the polymerization temperature can be measured by means of thermocouples or RTD, the polymerization pressure can be measured by means of a pressure transducer, the number of moles of hydrogen, the first monomer and the second monomer in the vapor phase in the reactor can be determined by gas chromatographic analysis of vapor withdrawn from the reactor, the number of moles of the first and second metals introduced into the reactor can be determined by flow meters located in the respective lines into the reactor
- 25

- 24 -

and the composition of the catalyst and cocatalyst being introduced; the mass inventory of the reactor can be determined from empirical correlations from the direct proportionality of the total mass inventory W in the reactor to the amperage required to drive the drive shaft in the reactor or other convenient conventional instrumentation, and the rates of introduction of the quench liquid and vapor recycle into the reactor can be determined by flow meters for the respective lines to the reactor.

The values of H_p and H_v in a particular reactor depend on the specific temperature, pressure, and type of polymerization reaction occurring in that reactor. For example, when a homopolymer of propylene is being formed, H_p is 24.9 kcal/mole, and propylene is typically employed as the quench liquid and has an H_v of 3 kcal/mole. When a copolymer of propylene and ethylene is being formed, H_p depends on the specific composition of the copolymer being formed and is typically 24.9-25.4 kcal/mole, and a mixture of propylene and ethylene is typically employed as the quench liquid and has an H_v which depends on the relative amounts of propylene and ethylene and is typically 3-4 kcal/mole.

The values of α , β , γ , δ , r , r_2 and r_3 in Equations 4-9 for homopolymers, random copolymers and impact copolymers are presented in Table 1.

TABLE 1

| Coefficient | Homopolymer | Random Copolymer | Impact Copolymer |
|-------------|--|--|--|
| α | 16-19 | 16-19 | 16-19 |
| β | 4000-7000 | 4000-7000 | 4000-7000 |
| γ | 0.9-1.6 | 0.9-1.6 | 0.9-1.6 |
| δ | 1.0×10^{-4} - 5.0×10^{-4} | 1.0×10^{-4} - 5.0×10^{-4} | 1.0×10^{-4} - 5.0×10^{-4} |
| r_1 | 0 | 0.1 - 0.3 | 0.1 - 0.3 |
| r_2 | 0 | 0 | 1.0 - 5.0 |
| r_3 | 0 | 0 | 0.0 - 1.0 |

From the aforesaid measurements, constants and relationships, R_z , W_z and τ_z for each zone in a particular reactor are determined using

- 25 -

Equations 1, 2 and 3, respectively and then the instantaneous value of at least one of $\ln MFR_i$ or $Wt.\%II_i$ is then calculated for such reactor using Equations 4 or 5, respectively. These values are then inserted in Equation 6 to calculate the value of X_t^N for the particulate polymer product withdrawn from such reactor. X_t^N can be either $\ln(MFR_i)$ or $Wt.\%II_i$.

The value of the property calculated in Equation 6 is then compared to a pre-determined, set point value for that property, and in response to the difference between the calculated and pre-determined, set point values of that property, an adjustment is made to reduce such difference to or below an acceptable level therefor. Typically, the adjustment is determined by a proportional integral controller or a proportional integral derivative controller.

The operating variables to be adjusted depend upon the identity of the property being controlled. In particular, when the adjustment is to be made in response to the difference between the calculated and pre-determined set point values of the melt flow rate, at least one of temperature, H_2/I , II/I , M_{II}/M_I , L_z or G_z/L_z , preferably H_2/I or M_{II}/M_I , and more preferably H_2/I , is adjusted in order to reduce or minimize the difference. For example, to increase the melt flow rate, the ratio H_2/I is increased. When the adjustment is to be made in response to the difference between the calculated and pre-determined set points values of the $Wt.\%II$, at least one of II/I , L_z or G_z/L_z , preferably II/I , is adjusted in order to reduce or minimize the difference. For example, to increase the $Wt.\%II$, while maintaining the MFR at a constant value, II/I is increased and H_2/I is decreased.

Equations 1 and 6 were derived from mass and energy balances around each zone of each reactor. Equations 2 and 3 are definitions, and Equations 4 and 5 were derived from a kinetic model of the polymerization process. Equations 1-6 illustrate the relationships, for each reactor employed, between (a) the melt flow rate of the particulate polymer (homopolymer or copolymer) product withdrawn from such reactor and (b) a first set of parameters comprising the rates of introduction of quench liquid and vapor recycle into each zone of such reactor, the heat of polymerization in such reactor, the latent heat of vaporization of the quench liquid in such reactor, the total mass inventory of particulate product in such reactor and the fraction in each zone of such reactor of the aforesaid total mass inventory in such reactor, the mole ratio of hydrogen to the first

- 26 -

monomer in the vapor phase in such reactor, the mole ratio of the second monomer to the first monomer in the vapor phase in such reactor, the mole ratio of the aforesaid second metal to the aforesaid first metal introduced into the reactor, the molecular weights of the first and second monomers, the relative reactivities of the first and second monomers in the formation of the copolymer, if copolymerization is occurring, and the reactor temperature and pressure.

Equations 1-6 also illustrate the relationships for each reactor employed, between (a) the weight percent of the second monomer in the particulate copolymer withdrawn from such reactor, if copolymerization is occurring, and (b) a second set of parameters comprising the rates of introduction of quench liquid and vapor recycle into each zone of such reactor, the heat of polymerization in such reactor, the latent heat of vaporization of the quench liquid in such reactor, the total mass inventory of particulate product in such reactor and the fraction in each zone of such reactor of the aforesaid total mass inventory in such reactor, the mole ratio of second monomer to the first monomer in the vapor phase in such reactor, the relative reactivities of the first and second monomers in the formation of the copolymer, if copolymerization is occurring, and the molecular weights of the first and second monomers.

Measurable values of L_z , G_z , W , f_z , T , H_2 , I , II , M_I and M_{II} , reported or determined values of H_p , H_v , MW_I and MW_{II} , and empirically determined values of α , β , γ , δ , r_1 , r_2 and r_3 are inserted in Equations 1-5 in order to determine values of R_z , W_z and τ_z and values of the instantaneous MFR and Wt.%II for each zone of such reactor. These values are then inserted in Equation 6 to calculate the value of the property X_t^N for the particulate polymer product withdrawn from the reactor. X_t^N can be either $\ln(MFR_t^N)$ or $Wt.\%II_t^N$.

Thus, for a single reactor having four zones, $\ln(MFR_t^4)$ is calculated as follows:

- 27 -

$$\ln(\text{MFR}_t^4) = \frac{\Delta t}{\tau_4 + \Delta t} \left[\left(\frac{R_4}{\sum_{z=1}^4 R_z} \right) (\ln(\text{MFR}_t)) + \left(\frac{\sum_{z=1}^3 R_z}{\sum_{z=1}^4 R_z} \right) (\ln(\text{MFR}_t^3)) \right] + \left(\frac{\tau_4}{\tau_4 + \Delta t} \right) (\ln(\text{MFR}_{t-\Delta t}^4)) \quad (\text{Equation 10})$$

However, solving Equation (10) involves calculating the instantaneous value of $\ln(\text{MFR}_t)$ for zone 3 of the reactor, which in turn necessitates calculating the instantaneous values of $\ln(\text{MFR}_t)$ for each of zones 1 and 2, as follows:

For zone 3

$$\ln(\text{MFR}_t^3) = \frac{\Delta t}{\tau_3 + \Delta t} \left[\left(\frac{R_3}{\sum_{z=1}^3 R_z} \right) \ln(\text{MFR}_t) + \left(\frac{\sum_{z=1}^2 R_z}{\sum_{z=1}^3 R_z} \right) (\ln(\text{MFR}_t^2)) \right] + \left(\frac{\tau_3}{\tau_3 + \Delta t} \right) (\ln(\text{MFR}_{t-\Delta t}^3)) \quad (\text{Equation 11})$$

10

For zone 2

$$\ln(\text{MFR}_t^2) = \frac{\Delta t}{\tau_2 + \Delta t} \left[\left(\frac{R_2}{\sum_{z=1}^2 R_z} \right) \ln(\text{MFR}_t) + \left(\frac{\sum_{z=1}^1 R_z}{\sum_{z=1}^2 R_z} \right) (\ln(\text{MFR}_t^1)) \right] + \left(\frac{\tau_2}{\tau_2 + \Delta t} \right) (\ln(\text{MFR}_{t-\Delta t}^2)) \quad (\text{Equation 12})$$

For zone 1

$$\left(\ln(MFR_1^1) \right) = \left(\frac{\Delta t}{\tau_1 + \Delta t} \right) \left(\ln(MFR_1) \right) + \left(\frac{\tau_1}{\tau_1 + \Delta t} \right) \left(\ln(MFR_{1-\Delta t}^1) \right)$$

(Equation 13)

5 When, for example, two reactors in series are employed, the calculations illustrated by Equations 1-6 must be made for each reactor. For example, in the manufacture of an impact copolymer of propylene and ethylene, the first reactor is employed to polymerize propylene to form a homopolymer of propylene, which is then transferred to the second reactor
 10 where a random copolymer of propylene and ethylene is formed in the presence of and into the homopolymer from the first reactor. In such case, for the first reactor, Equation 4 simplifies to Equation 9, and Equation 5 is not applicable. Thus, the results from Equations 1-3 and 9 are employed in Equation 6 to calculate $\ln(MFR_1^N)$ for the particulate homopolymer product
 15 produced in and withdrawn from the first reactor. For the second reactor, the results of Equation 1-4 are employed in Equation 6 to calculate $\ln(MFR_1^N)$ for the random copolymer segment produced in and withdrawn from the second reactor. For the second reactor, the zones are numbered starting with the next integer after the number of the last zone in the first reactor. Thus, N is the number of the last zone in the second reactor.
 20 The $\ln(MFR_1^N)$ for the composite impact copolymer is the weighted

sum of the $\ln(MFR)$ of the polymer segment formed in each reactor. With J being the fraction of the impact copolymer represented by the random segment produced in the second reactor, 1-J is the fraction of the impact
 25 copolymer represented by the homopolymer segment produced in the first reactor. Thus, $\ln(MFR_1^N)$ of the impact copolymer is the sum of (1) the product of (1-J) multiplied by the value of $\ln(MFR_1^N)$ for the first reactor and
 (2) the product of J multiplied by the value of $\ln(MFR_1^N)$ for the second reactor. By contrast, the value of Wt.%II for an impact copolymer is
 30 determined directly from Equations 1-3, 5 and 6 for the second reactor.

Turning now to Figure 2 for an illustration of an important benefit of the method of the present invention, being a simulation involving a single

- 29 -

substantially horizontal, quench cooled, stirred bed reactor containing four
aforesaid zones to make polypropylene homopolymer. Several options for
increasing the ratio of hydrogen to propylene from that needed to make a
homopolymer grade having an MFR of 3 to that needed to make of
5 homopolymer grade having an MFR of 10, were tested. Figure 2 contains
plots of values of $\ln(\text{MFR}_t^4)$ calculated from Equation 6 using results from
Equations 1-3 and 9, versus the time, measured from the time when the
change in the hydrogen to propylene ratio was implemented.

In the base case (no overshoot), the aforesaid hydrogen to propylene
10 ratio was increased in a conventional step change from the value therefor
needed to produce the polymer with an MFR of 3 at steady state to the value
therefor needed to produce the polymer with an MFR of 10 at steady state.
In three other cases, the value of the aforesaid ratio was increased to a level
above the value thereof needed to produce polypropylene having an MFR of
15 10 at steady state, in an effort to reduce the transition time needed to come to
steady state. Overshoot durations of 10, 20 and 40 minutes were employed to
illustrate that the overshoot duration must be optimized in order to achieve
the deserved reduction in transition time from the first steady state for
production of polypropylene having an MFR of 3 to the second steady state
20 for production of polypropylene having an MFR of 10 at steady state.
Selecting the degree of overshoot of the hydrogen to propylene ratio from
Equation 9 as the aforesaid ratio needed to produce an instantaneous MFR of
30, calculated values of (MFR_t^4) from Equation 6 plotted in Figure 2 illustrate
clearly that the beneficial effect of overshooting in reducing the transition
25 time.

From the above description, it is apparent that the objects of the
present invention have been achieved. While only certain embodiments
have been set forth, alternative embodiments and various modifications
will be apparent from the above description to those skilled in the art. These
30 alternatives are considered equivalent and within the spirit and scope of the
present invention.

Having described the invention, what is claimed is:

- 30 -

1. A method for the vapor-phase polymerization of at least one alpha-olefin monomer in a reaction mixture comprising a first alpha-olefin monomer and, if copolymerization is occurring, a second alpha-olefin monomer, comprising: conducting the polymerization under
5 polymerization conditions of temperature and pressure in the presence of hydrogen and a catalyst system comprising a solid catalyst comprising a first metal and a cocatalyst comprising a second metal, in at least one reactor wherein in each such reactor at least a portion of the heat of polymerization is removed by evaporative cooling of a volatilizable quench liquid
10 comprising liquefied first monomer and if copolymerization is occurring, liquefied second monomer, and wherein each reactor is a substantially horizontal reactor of substantially circular cross-section containing a centrally-located drive shaft extending longitudinally through such reactor to which are attached a plurality of adjacently located paddles, which paddles
15 cause essentially no forward or backward movement of the particulate polymer product contained in such reactor and extend transversely within and to a short distance from the internal surfaces of such reactor; driving means in each such reactor for the drive shaft; one or more reactor off-gas outlets spaced along the topward part of each such reactor; a plurality of
20 vapor recycle inlets spaced along the bottomward part of each such reactor for recycle of unreacted first monomer and, if copolymerization is occurring unreacted second monomer; one or more catalyst addition inlets spaced along each such reactor; a plurality of quench liquid inlets spaced along the topward part of each such reactor whereby quench liquid can be introduced
25 into such reactor; and take-off means in each such reactor for said particulate polymer product at one or both ends of such reactor;

wherein the performance of the polymerization reaction is controlled in order to afford the production in each such reactor of a particulate polymer product having predetermined characteristics of at least one of the
30 melt flow rate thereof and the weight percent therein of the second monomer, if any, by a method comprising, for each reactor employed:

(a₁) determining relationships between the melt flow rate of the particulate polymer product withdrawn from such reactor, and a first set of parameters comprising the rates of introduction of quench liquid and vapor
35 recycle into each zone of such reactor, the heat of polymerization in such reactor, the latent heat of vaporization of the quench liquid in such reactor, the total mass inventory of particulate polymer product in such reactor and the fraction in each zone of such reactor of the aforesaid total mass.

- 31 -

inventory in such reactor, the mole ratio of hydrogen to the first monomer in the vapor phase in such reactor, the mole ratio of the second monomer to the first monomer in the vapor phase in such reactor, the mole ratio of the aforesaid second metal to the aforesaid first metal introduced into such reactor, the molecular weights of the first and second monomers, the relative reactivities of the first and second monomers in the formation of the copolymer if copolymerization occurs, and the temperature and pressure in such reactor;

(b₁) monitoring such first set of parameters;
(c₁) from the first set of parameters monitored in step (b₁) and the relationships from step (a₁), calculating the melt flow rate of the polymer withdrawn from such reactor; and

(d₁) adjusting at least one of the reactor operating variables within minimum and maximum constraints thereof to adjust the calculated melt flow rate of the polymer withdrawn from such reactor to a pre-determined set point level therefor, wherein such reactor variables are the mole ratio of the second monomer to the first monomer, if copolymerization is occurring, in the vapor phase in such reactor in the range of from about 0.0005 to about 0.5, the mole ratio of hydrogen to the first monomer in the vapor phase in such reactor in the range of from about 0.0005 to about 0.08, the mole ratio of the second metal to the first metal introduced into such reactor in the range of from about 14 to about 200, the rate of introduction of quench liquid into each zone of such reactor in the range of from about 5 kg/sec to about 50 kg/sec, the ratio of the rate of introduction of the vapor recycle to the rate of introduction of quench liquid into each zone of such reactor in the range of from about 0.05 to about 0.3, and the temperature in such reactor in the range of from about 20°C to about 100°C.

2. The method of Claim 1 which additionally comprises, for each reactor employed:

(a₂) determining relationships between the weight percent of the second monomer in the particulate polymer product, if copolymerization occurs, withdrawn from such reactor, and a second set of parameters comprising the rates of introduction of quench liquid and vapor recycle into each zone of such reactor, the heat of polymerization in such reactor, the latent heat of vaporization of the quench liquid in such reactor, the total mass inventory of particulate copolymer product in such reactor, and the fraction in each zone of such reactor of the aforesaid total mass inventory in such reactor, the mole ratio of second monomer to the first monomer in the

- 32 -

vapor phase in such reactor, the relative reactivities of the first and second monomers in the formation of the copolymer if copolymerization occurs, and the molecular weights of the first and second monomers;

(b₂) monitoring such second set of parameters;

5 (c₂) from the second set of parameters monitored in step (b₂) and the relationships from step (a₂), calculating the weight percent of the second monomer in the copolymer product withdrawn from such reactor; and

(d₂) adjusting at least one of the reactor operating variables within minimum and maximum constraints thereof to adjust the weight percent of
10 second monomer in the copolymer withdrawn from such reactor to a pre-determined, set point level therefor, wherein such reactor variables are the mole ratio of the second monomer to the first monomer in the vapor phase in such reactor in the range of from about 0.0005 to about 0.5, the rate of introduction of the quench liquid into each zone of such reactor in the range
15 of from about 5 kg/sec to about 50 kg/sec, and the ratio of the rate of introduction of the vapor recycle to the rate of introduction of quench liquid into each zone of such reactor in the range of from about 0.05 to about 0.3,

3. The method of Claim 1 wherein, for each reactor employed:

(a₃) the temperature and pressure in such reactor are determined;

20 (b₃) the mole ratios of the following are determined:

(1) hydrogen to the first monomer in the vapor phase in such reactor,

(2) the second monomer to the first monomer in the vapor phase in such reactor, and

25 (3) the aforesaid second metal to the aforesaid first metal introduced into such reactor;

(c₃) the rates in parts by weight per unit of time of the introduction of each of the quench liquid and the vapor recycle into each zone of such reactor are determined;

30 (d₃) the rate of production of the particulate polymer product in each zone of such reactor is determined as follows:

$$R_z = \frac{L_z(1 + G_z/L_z)}{1 + H_p/H_v} \quad (\text{Equation 1})$$

wherein the subscript Z is the number of the zone and ranges from 1 to N, R_z is the production rate of the particulate polymer product in zone Z, L_z is
35 the rate of introduction of the quench liquid into zone Z, G_z is the rate of introduction of the vapor recycle into zone Z, H_p is the heat of

- 33 -

polymerization in zone Z, and H_v is the latent heat of vaporization of the quench liquid in zone Z;

- (e₃) the mass inventory of particulate polymer product in each zone of such reactor is determined from the fraction in each zone of the total mass inventory of particulate polymer product in such reactor and the total mass inventory of particulate polymer product in such reactor, as follows:

$$W_z = f_z W$$

(Equation 2)

- wherein W is the aforesaid total mass inventory in such reactor, f_z is the aforesaid fraction in the zone Z in such reactor, and W_z is the aforesaid mass inventory in such zone Z;

(f₃) the time constant for each zone of such reactor is determined, as follows:

$$\tau_z = \frac{W_z}{\sum_{z=1}^Z R_z} \quad (\text{Equation 3})$$

- wherein τ_z is the time constant in zone Z.

- (g₃) at least one of the instantaneous melt flow rate and the instantaneous weight percent of the second monomer in the particulate polymer product being produced instantaneously within such reactor at any instant of steady-state or transition operation is determined, as follows:

$$\ln(MFR_1) = -\alpha - \frac{\beta}{T} + \gamma \ln \left[\left(\frac{H_2}{I} \right) + \delta \left(\frac{M_2}{M_1} \right) \right] + \gamma \ln \left[\frac{(r_2 + r_2 \alpha / D) (MW_{II})}{r_2 (MW_{II}) + \alpha / D (MW_I) + (MW_{II}) + r_1 \alpha / D^2 (MW_I)} \right] \quad (\text{Equation 4})$$

$$\text{Wt. \% II} = 100 \left[\frac{(r_1 (\alpha / D)^2 + (\alpha / D)) (MW_I)}{(r_1 (\alpha / D)^2 + (\alpha / D)) (MW_I) + (r_2 + (\alpha / D)) (MW_{II})} \right] \quad (\text{Equation 5})$$

- 34 -

where MFR_i is the melt instantaneous flow rate of the polymer being produced within such reactor at that instant, $Wt.\%II_i$ is the instantaneous weight percent of the second monomer in the polymer product being produced in such reactor at that instant, T is the temperature, H_2/I is the mole ratio of hydrogen to the first monomer in the vapor phase in such reactor, M_2/M_1 is the mole ratio of the aforesaid second metal to the aforesaid first metal introduced into such reactor, II/I is the mole ratio of the second monomer to the first monomer in the vapor phase in such reactor, MW_I is the molecular weight of the first monomer, MW_{II} is the molecular weight of the second monomer, and $\alpha, \beta, \gamma, \delta, r_1, r_2$ and r_3 are catalyst and reactor system dependant constants which are determined by experimental data;

(h₃) the value of X is determined for the polymer product withdrawn from such reactor, as follows:

$$X_t^N = \left(\frac{\Delta t}{\tau_N + \Delta t} \right) \left[\left(\frac{R_N}{\sum_{z=1}^N R_z} \right) X_i + \left(\frac{\sum_{z=1}^{N-1} R_z}{\sum_{z=1}^N R_z} \right) X_t^{N-1} \right] + \left(\frac{\tau_N}{\tau_N + \Delta t} \right) X_{t-\Delta t}^N$$

(Equation 6)

wherein N is the number of the last zone in such reactor, $N-1$ is the number of the preceding zone, X_t^N is the value of the $\ln(MFR_t)$, or $Wt.\%II_t$, of the particulate polymer product withdrawn from zone N at time t , Δt is the sampling time interval, X_i is the instantaneous value of the $\ln(MFR_i)$, or $Wt.\%II_i$ determined in Equations 4 or 5, respectively, $X_{t-\Delta t}^N$ is the calculated value of X for the same zone N but for the immediately preceding sampling interval, and X_t^{N-1} is the calculated value of X for the same sampling interval, but for zone $N-1$; and

(i₃) determining the difference between X_t^N for MFR_t^N or $Wt.\%II_t^N$, calculated in Equation 6 and the predetermined set point value therefor and in response to the determined difference, adjusting

(1) at least one of the temperature, II/I , H_2/I , M_2/M_1 , L_2 , or G_2/L_2 for MFR_t^N , or

(2) at least one of the Π/I , L_2 , or G_2/L_2 for $Wt.\%II_1$;

in order to reduce the difference between such determined and predetermined set point values to a predetermined acceptable level therefor,

4. The method of Claim 1 wherein the first monomer is propylene and homopolymerization occurs.

5. The method of Claim 4 wherein the mole ratio of hydrogen to propylene in the vapor phase in the reactor is in the range of from about 0.002 to about 0.04.

6. The method of Claim 1 wherein a single reactor is employed, the first monomer is propylene and the second monomer is ethylene and copolymerization occurs and a random copolymer is formed.

7. The method of Claim 6 wherein the mole ratio of hydrogen to propylene in the vapor phase in each reactor is in the range of from about 0.002 to about 0.04 and the mole ratio of ethylene to propylene in the range of from about 0.004 to about 0.03.

8. The method of Claim 1 wherein the first metal is titanium.

9. The method of Claim 1 wherein the second metal is aluminum.

10. The method of Claim 8 wherein the second metal is aluminum.

11. The method of Claim 10 wherein the mole ratio of aluminum to titanium introduced into each reactor is in the range of from about 60 to about 120.

12. The method of Claim 1 wherein two reactors are employed in series, and a homopolymer of propylene is prepared in the first reactor and is passed into the second reactor where an impact copolymer is formed by the copolymerization of propylene and ethylene in the presence of the homopolymer of propylene.

13. The method of Claim 12 wherein in the second reactor the mole ratio of ethylene to propylene in the vapor phase is in the range of from about 0.2 to about 0.4.





Fig. 1

2/2

Fig. 2



SUBSTITUTE SHEET

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/05051

| | | |
|--|--|-------------------------------------|
| I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶ | | |
| According to International Patent Classification (IPC) or to both National Classification and IPC | | |
| Int.Cl. 5 C08F2/00; B01J19/00; C08F2/34 | | |
| II. FIELDS SEARCHED | | |
| Minimum Documentation Searched ⁷ | | |
| Classification System | Classification Symbols | |
| Int.Cl. 5 | C08F ; B01J | |
| Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸ | | |
| | | |
| III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹ | | |
| Category ¹⁰ | Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹² | Relevant to Claim No. ¹³ |
| A | EP,A,0 328 826 (BP CHEMICALS) 23 August 1989 see examples 1,2 --- | 1 |
| A | EP,A,0 257 316 (UNION CARBIDE CORPORATION) 2 March 1988 see the whole document --- | 1 |
| A | EP,A,0 318 609 (UNION CARBIDE CORPORATION) 7 June 1989 see the whole document --- | 1 |
| A | PATENT ABSTRACTS OF JAPAN 29 August 1987 & JP,A,62 070 404 (MITSUI PETROCHEMICAL INDUSTRIES) 31 March 1987 see abstract. --- | 1 |
| -/-- | | |
| <p>¹⁰ Special categories of cited documents : ^{"A"} document defining the general state of the art which is not considered to be of particular relevance ^{"E"} earlier document but published on or after the international filing date ^{"L"} document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) ^{"O"} document referring to an oral disclosure, use, exhibition or other means ^{"P"} document published prior to the international filing date but later than the priority date claimed</p> <p>^{"T"} later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention ^{"X"} document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step ^{"Y"} document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. ^{"A"} document member of the same patent family</p> | | |
| IV. CERTIFICATION | | |
| Date of the Actual Completion of the International Search | Date of Mailing of this International Search Report | |
| 06 OCTOBER 1993 | 20. 10. 93 | |
| International Searching Authority | Signature of Authorized Officer | |
| EUROPEAN PATENT OFFICE | FISCHER B.R. | |

| III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET) | | |
|--|---|-----------------------|
| Category * | Citation of Document, with indication, where appropriate, of the relevant passages | Relevant to Claim No. |
| A | EP,A,0 398 706 (E.I DU PONT DE NEMOURS) 22 November 1990 see page 1 - page 9 see figure 1 ----- | 1 |

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

US 9305051
SA 76125

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

06/10/93

| Patent document cited in search report | Publication date | Patent family member(s) | Publication date |
|---|---------------------|----------------------------|---------------------|
| EP-A-0328826 | 23-08-89 | FR-A- 2625506 | 07-07-89 |
| | | WO-A- 8906244 | 13-07-89 |
| | | JP-T- 2502835 | 06-09-90 |
| | | US-A- 5155184 | 13-10-92 |
| ----- | | | |
| EP-A-0257316 | 02-03-88 | US-A- 4956426 | 11-09-90 |
| | | CA-A- 1296136 | 18-02-92 |
| | | JP-A- 63035612 | 16-02-88 |
| ----- | | | |
| EP-A-0318609 | 07-06-89 | None | |
| ----- | | | |
| EP-A-0398706 | 22-11-90 | US-A- 5065336 | 12-11-91 |
| | | JP-A- 3115302 | 16-05-91 |
| ----- | | | |